

This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

DOC No: AM-18033-TDS-0004 Rev. No. 1.0 Page 1 of 7

TITLE: TECHNICAL DATA SHEET

Description: Material Purchase Specification – Thabana **Date: See Signature Block Pipestore Extension** Technical Data Sheet for the supply of: ASME SA-312M Seamless, Welded and Heavily Cold Worked Austenitic Stainless-Steel Pipes Name Signature Date GJ van Heerden Prepared G.J. van Heerden 20/11/2023 Mechanical Engineer TP Choeu Reviewed 2023/11/21 QC Manager Reviewed **CIK Corbitt** 2023/11/22 QA Manager Approved MD van Heerden **MO Manager**

REVISION HISTORY

Rev	Date	Description of changes
1.0	See signature block	First issue

1 SCOPE

- 1.1. Supplying of Seamless or Welded Austenitic Stainless-Steel Pipes, of Grade TP304L, shall conform to all the applicable requirements of:
 - 1.1.1. SA-312M, Specification for Seamless, Welded and Heavily Cold Worked Austenitic Stainless-Steel Pipes, ref. [1];
 - 1.1.2. SA-999M, Specification for General Requirements for Alloy and Stainless-Steel Pipe, ref. [2];
- 1.2 The supplier shall supply the material in compliance with this TDS.



This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

DOC No: AM-18033-TDS-0004 Rev. No. 1.0 Page 2 of 7

TITLE: TECHNICAL DATA SHEET

2 APPLICABLE DOCUMENTS

[1] ASME BPVC Section II, Part A, SA-312M, 2019 Edition.

[2] ASME BPVC Section II, Part A, SA-999M, 2019 Edition.

[3] Doc No: AM-IMS-MAN-0001, Rev. 2.0, SHEQ Manual.

3 BASIC REQUIREMENTS

3.1	Ordering	Information:
J. 1	Ciucilia	IIIIOIIIIauoii.

3.1.1 Code of Manufacturing: ASME Section II, Part A, 2019 Edition,

ref. [1];

3.1.2 Material Specification: SA-312M, ref. [1];

3.1.3 ASTM Designation: Acceptable ASTM Editions – 1988a

through 2015 with exceptions as stated in Table II-200-1 of ASME

Section II, Part A;

3.1.4 Name of Material: Austenitic Stainless-Steel

(UNS designation: S30403);

3.1.5 Process: Welded;

3.1.6 Grade: TP304L;

3.1.7 Pipe Schedule: As per Purchase Order;

3.1.8 Size: As per Purchase Order;

3.1.9 Length: As per Purchase Order;

3.1.10 Quantity: As per Purchase Order;

3.1.11 End Finish: Shall conform to par. 15 of SA-999M;

3.1.12 Test Report Required: Yes, as per Section 16 of this TDS;

3.1.13 Certification: Certification is required as per

Section 16 of this TDS;

3.1.14 Optional Requirements: Hydrostatic or Non-destructive Electric

Test Requirements as per par. 12 of

SA - 312M, ref. [1];

3.1.15 Supplementary Requirements: None;



This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

DOC No: AM-18033-TDS-0004 Rev. No. 1.0 Page 3 of 7
TITLE: TECHNICAL DATA SHEET

3.1.16 Special Requirements:

As specified in this TDS.

- 3.2 SI units of measure shall be used.
- 3.3 All documents shall be provided in the English language.
- 3.4 No Code Cases are allowed.
- 3.5 Notification and Hold Points, if any, shall be as given on the Purchase Order.

4 MANUFACTURING PROCESS

4.1 Shall conform to par. 6 of SA-312M, ref. [1], and par. 3 of SA-999M, ref. [2].

5 CHEMICAL COMPOSITION REQUIREMENTS

- 5.1 Shall comply with the chemical composition prescribed in par. 7 and Table 1 of SA-312M, ref. [1], for Grade TP304L.
- 5.2 Analysis shall be conducted as per par. 6 of SA-999M, ref. [2].

6 HEAT TREATMENT

6.1 Shall conform to par. 6.2 and Table 2 of SA-312M, ref. [1].

7 MECHANICAL PROPERTIES

- 7.1 All material mechanical tests and property requirements, for Grade TP304L, shall comply with par. 11 of SA-312, ref. [1], and pars. 7, 8 and 20 of SA-999M, ref. [2]. The required tests are listed below:
 - 7.1.1 Tensile test Shall conform to par. 10 and Table 4 of SA-312M, ref. [1];
 - 7.1.2 Flattening test Shall conform to par. 11.3 of SA-312M, ref. [1], and par. 21 of SA-999M, ref. [2].

8 WORKMANSHIP, FINISH AND APPEARANCE

8.1 Shall conform to par. 14 of SA-312M, ref. [1], and pars. 9, 10, 11, 12, 13, 14, 15 and 16 of SA-999M, ref. [2].



This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

 DOC No:
 AM-18033-TDS-0004
 Rev. No. 1.0
 Page
 4
 of
 7

 TITLE:
 TECHNICAL DATA SHEET

9 FRACTURE TOUGHNESS REQUIREMENTS

9.1 Impact tests are not required, as exempted by the Mechanical Design Code for the Thabana Pipestore Extension Project.

10 EXAMINATIONS AND REPAIRS

- 10.1 Hydrostatic or non-destructive electric tests shall be performed according to par. 12 of SA-312M, ref. [1], and par. 22 of SA-999M, ref. [2].
- 10.2 Repair by welding is not permitted.

11 SUPPLEMENTARY AND ADDITIONAL REQUIREMENTS

11.1 As specified on the Purchase Order.

12 NON-CONFORMANCES

- 12.1 The Purchaser shall be notified by non-conformance reports of any condition that does not comply with the requirements of this TDS, the Purchase Order, Applicable Codes and Standards as listed in Section 2 of this document, also during the delivery process, or detection of any Counterfeit, Fraudulent or Suspect Items.
- 12.2 Disposition of the material with non-conformances require approval from the Purchaser.

13 IDENTIFICATION AND MARKING OF MATERIAL

- 13.1 Material shall be marked in accordance with:
 - 13.1.1 Par. 17 of SA-312, ref. [1], and par. 26 of SA-999M, ref. [2];
 - 13.1.2 Requirements of this TDS.
- 13.2 At minimum the marking shall include:
 - 13.2.1 Specification Number (SA-312M);
 - 13.2.2 Grade (TP304L);
 - 13.2.3 Size (As per Purchase Order);



This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

 DOC No:
 AM-18033-TDS-0004
 Rev. No. 1.0
 Page
 5
 7

 TITLE:
 TECHNICAL DATA SHEET

- 13.2.4 Piping Schedule;
- 13.2.5 Heat number:
- 13.2.6 Heat treatment process (As per Section 6 of this TDS);
- 13.2.7 Manufacturer's name or identification mark.
- 13.3 Photos of the applied marking on the material shall be sent to the purchaser for acceptance prior to packaging and shipping.
- 13.4 All items shall be marked as per Purchase Order item reference and quantities clearly marked with a waterproof marker and certification thereof shall be submitted to the Purchaser.

14 HANDLING, PACKAGING AND DELIVERY

- 14.1 Handling, Packaging and Delivery shall comply with par. 27 of SA-999M, ref. [2].
- 14.2 The Supplier shall not dispatch material from its works until it has received the Purchaser's written acceptance of the Material Test Report (MTR).
- 14.3 All material supplied shall have a good surface finish
- 14.4 All items shall be protected from damage and contamination (inside and outside) from chemicals or solids that are detrimental to the integrity and corrosion resistance of stainless-steel.
- 14.5 The Material Supplier shall provide suitable means to clearly identify the following information on the outside of the packaging:
 - 14.5.1 Material Specification, Class/Grade of Material;
 - 14.5.2 Overall weight of Package;
 - 14.5.3 Material Organisation's Name and Details.
- 14.6 Inspection and Release notes shall accompany all material for delivery. No material will be accepted without the abovementioned release notes.
- 14.7 It is important that the full complement of items listed in the Purchase Order is to be delivered as specified in the Purchase Order.



This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

DOC No: AM-18033-TDS-0004 Rev. No. 1.0 Page 6 of 7

TITLE: TECHNICAL DATA SHEET

15 RIGHT OF ACCESS

15.1 Access to the Supplier's and its Sub tier Supplier's facilities shall be provided to the Purchaser, Authorized Inspector or others authorized by the Purchaser including his customer and end user for surveillance, inspection, or audit.

16 DOCUMENTATION TO BE PROVIDED BY THE SUPPLIER

- 16.1 Copies of the material certificates for the material as required by par. 16 of SA 312M, ref. [1], par. 25 of SA-999M, ref. [2], and this TDS shall be submitted by email for acceptance by the Purchaser. No material shall be shipped without the Purchaser's acceptance of the certificates.
- 16.2 The manufacturer shall provide the test report in accordance with the requirements of par. 25 of ref. [2].
- 16.3 The Material certificate shall include, but not limited to test results and information as applicable:
 - 16.3.1 Description of material;
 - 16.3.2 Heat treatment type;
 - 16.3.3 Chemical Analyses results (heat and/or product);
 - 16.3.4 Tensile test/property results;
 - 16.3.5 Width in the gage length (if longitudinal strip tension tests were used);
 - 16.3.6 Hydrostatic test pressure or Non-destructive electric test method;
 - 16.3.7 Visual acceptance of material surfaces, cleanliness and packaging:
 - 16.3.8 Heat treatment report (if available);
 - 16.3.9 Clear reference to the producing mill or factory;
 - 16.3.10 A statement that the welded stainless-steel pipe was manufactured, sampled, tested, inspected, handled and packaged in accordance with the requirements of the material specification (SA-312M) and this TDS.
- 16.4 Legible copies of the original certificates from the Mill are required.
- 16.5 All material certificates and test reports shall be traceable to the material identification marking.



This document is the property of Necsa and shall not be used, reproduced, transmitted or disclosed without prior written permission

DOC No:	AM-18033-TDS-0004	Rev. No. 1.0	Page	7	of	7
TITLE:	TECHNIC	AL DATA SHEE	Т			

17	17 QUALITY ASSURANCE REQUIREMENTS					
	17.1	All general and specific Quality Assurance requirements stated in the Purchase Order and this TDS shall be met.				
	17.2	Comply with ref. [3].				
		r				
1						